

PRODUCT NAME	C. I. NO	Fastness			Application(plastic)				
		Heat resistance	Light resistance	Migration resistance	PVC	LDPE	HDPE	PP	ABS
P3176R Benzidine Yellow G	P. Y. 12	180	5	2-3	◎	◎	◎	○	X
P3122 Permanent Yellow GR	P. Y. 13	200	5-6	3	◎	◎	◎	○	X
P3188 Permanenet Yellow 2GS	P. Y. 14	200	5-6	2-3	◎	◎	◎	○	X
P3177 Permanent Yellow GG	P. Y. 17	210	6	3	◎	◎	◎	○	X
P3183 Permanent Yellow HR	P. Y. 83	220	7-8	5	◎	◎	◎	○	X
P3168 Monoazo Yellow WGP	P. Y. 168	240	7-8	5	◎	◎	◎	◎	○
P3193 Monoazp Yellow HRP	P. Y. 183	250	8	5	◎	◎	◎	◎	◎
P3180 Benzimidazolone Yellow	P. Y. 180	250	8	5	◎	◎	◎	◎	◎
P3191Fast Yellow HGR	P. Y. 191	250	8	5	◎	◎	◎	◎	◎
P3213Permanent Orange G	P. O. 13	180	6	3-4	◎	◎	◎	○	X
P3234Permanent Orange Rl	P. O. 34	220	6	4	◎	◎	◎	○	X
P3236Benzimidazolone Orange	P. O. 36	240	8	5	◎	◎	◎	◎	○
P3246Benzimidazolone Orange	P. O. 64	250	8	5	◎	◎	◎	◎	◎
P3581Fast scarlet BBN	P. R. 48:1	200	4	4	◎	◎	◎	○	X
P3582Fat Brilliant Red BBC	P. R. 48:2	220	4	4	◎	◎	◎	◎	X
P3583Fast Red BBS	P. R. 48:3	220	5	4-5	◎	◎	◎	◎	X
P3531Y Bronze RED C	P. R. 53:1	220	4	4	◎	◎	◎	○	X
P3571Lithol Rubine BK	P. R. 57:1	220	5	4	◎	◎	◎	○	X
P3573Permanent Red F3RK	P. R. 170	220	7-8	4	◎	◎	◎	○	X
P3575Permanent Red F5Rk	P. R. 170	220	7-8	4	◎	◎	◎	○	X
P3522 Quindo Red 122	P. R. 122	280	8	5	◎	◎	◎	◎	◎
P3554 DPP Red Bo	P. R. 254	280	8	5	◎	◎	◎	◎	◎
P3019 Quinacridone Violet	P. V. 19	280	8	5	◎	◎	◎	◎	◎
P3023B Permanent Violet RL	P. V. 23	250	8	5	◎	◎	◎	◎	X

◎ recommend ○ suitable X not suitable